

## Properties

### S1210

Glass fiber-reinforced PC/ABS resin (GF10%, UL94 HB)

Properties	Test methods	Test conditions	Units	
Mold shrinkage	ASTM D955	-	%	0.2-0.5
Tensile strength	ISO 527	-	MPa	72
Flexural strength	ISO 178	-	MPa	110
Flexural modulus	ISO 178	-	MPa	4000
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m2	11
Notched Izod impact strength	ASTM D256	23 deg C/6.4mm	J/m	110
Deflection temperature under load	ISO 75	1.80MPa	deg C	112
Deflection temperature under load	ASTM D648	1.82MPa/6.4mm	deg C	122
Coefficient of linear thermal expansion	ISO 11359	MD	X1E-5/deg C	6
Coefficient of linear thermal expansion	ISO 11359	TD	X1E-5/deg C	8
Flammability	UL94	-	-	HB
Dielectric strength	ASTM D149	1.5mm	MV/m	36
Arc resistance	ASTM D495	3.0mm	sec(PLC)	106(6)
Hot wire ignition	UL746A	1.5mm	sec(PLC)	54(2)
High ampere arc ignition	UL746A	1.5mm	(PLC)	29(3)
High voltage tracking rate	UL746A	3.0mm	mm/min(PLC)	94(3)
Comparative tracking index	IEC 112	3.0mm	V(PLC)	175(3)
Water absorption	ISO 62	-	%	0.3
Density	ISO 1183	-	g/cm3	1.20

Note

- Values are typical, not quality assured.
- UL recognition File No. of Daicel Polymer is E47773.

### Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
4-5hrs 90-110deg C	230-260	240-260	230-250	210-240	50-100	5-20	60-80